ASPOCRETE®

ENGINEERED TO LAST.

STANDARD

STANDARD

Polymer-modified grey adhesive for ceramic tiles on internal floors and walls.
IS 15477:2019 Type 1 'T' · EN 12004 C1T

PRODUCT DESCRIPTION

A polymer-integrated, grey cement composition-based adhesive for fixing ceramic tiles on internal floors and walls. Supplied premixed and ready to use across a wide range of substrates, it is water resistant and formulated to prevent cracking of tiles.

SUITABLE FOR

Material & Area

- High-porosity tiles (ceramic, porcelain, terracotta and quarry)
- Internal floor and wall applications
- Residential and commercial application
- Dry areas

Substrate

- Cement mortar beds
- Cement-based plaster
- Concrete surfaces
- Cement-based screed
- Cement terrazzo
- Brick masonry
- AAC block masonry
- Concrete block masonry

Conforms to IS 15477:2019 Type 1 'T' · EN 12004 C1T

PHYSICAL PROPERTIES @ 70°F (21°C) | Tile laying adhesive mixed with water

PARAMETERS	RESULTS
Colour	Grey
Mixing Ratio (Powder to Water)	3.5 : 1
Bulk Density	1.3 – 1.5 gm/cc
Mixing Density	1.7 – 1.9 gm/cc
Pot Life	> 2 hours
Open Time	~ 20 minutes
Adjustability	~ 20 minutes
Final Setting Time	24 hours
Max. Bed Thickness	12 mm
Time to Light Foot Traffic	16 – 24 hours
Ready for Grouting	24 hours
Ready for Use	14 days



ASPOCRETE®
ENGINEERED TO LAST.

STANDARD 20KG

STANDARD

ASPOCRETE®
ENGINEERED TO LAST.

PERFORMANCE PROPERTIES

IS 15477:2019


PARAMETER	REQUIREMENT	RESULT	TEST METHOD
Tensile Adhesion (Dry Conditon, 28 Days)	0.5 N/mm²	0.6 – 0.7 N/mm²	Annexure A, Clause 5.1
Shear Adhesion (Dry Conditon, 28 Days)	1 N/mm²	1.12 – 1.2 N/mm²	Annexure B, Clause 5.2
Slip Resistance	≤ 0.5 mm	0.3 – 0.35 mm	Annexure E, Clause 5.5

Standard adhesive mortar conforms to IS 15477:2019 Type 1T.

EN 12004

PARAMETER	REQUIREMENT	RESULT	TEST METHOD
Open Time	≥ 0.5 N/mm²	0.5 – 0.6 N/mm²	EN 1346
T – Slip Resistance	≤ 0.5 mm	0.35 – 0.44 mm	EN 1308
Tensile Adhesion Strength (C1)	≥ 0.5 N/mm²	0.55 – 0.6 N/mm²	EN 1348, Clause 8.2
Tensile Adhesion Strength (Afer Water Immersion)	≥ 0.5 N/mm²	0.55 – 0.6 N/mm²	EN 1348, Clause 8.3
Tensile Adhesion Strength (Heat Ageing)	≥ 0.5 N/mm²	0.55 – 0.6 N/mm²	EN 1348, Clause 8.4
Tensile Adhesion Strength (Freeze & Thaw)	≥ 0.5 N/mm²	0.55 – 0.6 N/mm²	EN 1348, Clause 8.5

Standard adhesive mortar conforms to EN 12004 C1T / ISO 13007.



STANDARD

ASPOCRETE®
ENGINEERED TO LAST.

APPLICATION PROCEDURE

1 : Surface Preparation

All surfaces must conform to the dimensional stability requirements outlined in IS 1443-2018.

Surfaces should be level, properly cured, undamaged, compact, rigid, resistant, dry, free from any debonding agents, and protected against damp rising.

Pre-wet or dampen highly absorbent concrete surface with good quality fresh water.

02 : Mixing

Use 5-6 litres of potable water for every 20 kg of adhesive.

Pour the minimum recommended amount of potable water into a clean mixing container, then gradually add dry mix product to the water (not vice versa) while continuously mixing with a low-speed electric single-paddle (spiral) mixer ata speed of <500 rpm.

Mix thoroughly for 2-3 minutes until a uniformly coloured, smooth mixture is achieved. Allow the mixed product to mature for 4-5 minutes without stirring, then remix for 15seconds just before using.

Avoid over-mixing to minimise air entrainment.

03 : Application

Apply the adhesive with the flat side of the trowel using a scraping motion, then apply additional mortar with the notched edge of the trowel.

For large-size tiles with sides greater than 2 feet, apply additional adhesive to the back of the tile with the flat side of the trowel.

Occasionally inspect that tiles are properly stuck; if the adhesive is non-sticky, remove and replace with fresh adhesive, then tap the tile with a rubber mallet to fully bed it.

Create elastic expansion joints: 5 mm at every 10 m^2 for external applications, 3 mm at every 25 m^2 for internal applications, and 3 mm every 8 m in long, narrow runs. Always respect structural, fractionizing and perimeter joints.

04 : Cleaning

Clean any excess adhesive from the tile surface and grout lines immediately with a damp sponge or cloth.

05 : Grouting

Carry out grouting after 24 hours of tiling, using an appropriate cementitious or epoxy grout from the Aspocrete range.



COVERAGE

55 – 60 sq.ft per 20 kg bag at 3 mm bed thickness, Using a 6mm x 6mm square-notched trowel.

STANDARD

ASPOCRETE®
ENGINEERED TO LAST.

SHELF LIFE

12 months from date of manufacture, if stored in a cool, dry place in original unopened packaging.

LIMITATIONS

Adhesives and grouts for tiles are not replacements for waterproof membranes. Where a waterproof membrane is required, use an Aspocrete waterproofing product, or any other suitable waterproofing product available in the market.

SAFETY PRECAUTIONS

- Keep out of reach of children.
- Wear suitable protective clothing, gloves, and eye/faceprotection.
- After contact with the skin, wash immediately with plenty of clean water.
- In case of eye contact, rinse immediately with plenty of clean water and seek medical advice.



IMPORTANT NOTES

- Always add powder to water, not water to powder.
- Do not add excess water beyond the recommended quantity.
- Do not add extra cement or sand to the adhesive, as it can disturb the product's intended formulation and compromise performance.
- Do not use on wet screed — the surface must be fully cured (28 days).
- Do not use the adhesive to correct surface irregularities greater than 12 mm (may extend to 15 mm in limited extent).
- For heavy stone or large tiles at more than 3 m height, the applicator must evaluate an additional mechanical fastening system (such as steel hooks fastened to the substrate).
- Protect freshly laid tiles from direct rainfall and foot traffic for at least 24 hours.
- Leave a gap between tiles using spacers and fill gaps with Aspocrete tile grout.
- It is mandatory to use an appropriately sized notched trowel to achieve the required adhesive thickness.
- It is advisable to prime highly absorbent substrates or tile/stone backs with a suitable bonding primer before application.
- Do not use on deformable substrates or substrates subject to vibration.

PLOT NO. 14P, 25P AND 15P1, 24P1, SY NO. 381 PART, KIADB INDUSTRIAL AREA, MANVI, RAICHUR, KARNATAKA - 584123

business@aspocrete.com www.aspocrete.com

Specifications may be modified without prior notice. The displayed results are representative and based on the testing procedures employed. Real-world performance will be influenced by installation technique and on-site conditions.